

ABSTRACT

The present invention provides methods for producing an ethylene-vinyl acetate copolymer and a saponified product thereof that can inhibit
5 visible imperfections (particularly discoloration) at the time of molding by improving the process for recovering vinyl acetate. When the alcohol-based solvent to be blown in when recovering vinyl acetate is deoxidized so that its oxygen concentration becomes not more than 60 ppm, discoloration of a molded product of the above saponified product due to oxygen can be
10 inhibited.